




| Technical parameter | Standard | Unit | Result |
|--|----------------|---|--------------------------------------|
| DESCRIPTION: Acoustic vinyl sheet floor with closed cell foam backing | | | |
| Construction | | | heterogeneous |
| Total thickness | EN 428 | mm | 3,2 |
| Wear layer thickness | EN 429 | mm | 0,55 |
| Width of roll | EN 426 | m | 2 |
| Length of roll | EN 426 | lm | 20 |
| Total weight | EN 430 | kg/m2 | 2,5 |
| CLASSIFICATION | | | |
| Product specification | EN 651 | | ✓ |
| European classification | EN 685 | class | 33/42 |
| Classement UPEC | NF EN 651 | class | U3P3E2/3C2 |
| Residual indentation | EN 433 | max. mm | 0,2 |
| Dimensional stability | EN 434 | max. % | 0,2 |
| Light fastness | EN 20105 B02 | grade | 6 |
| PERFORMANCE | | | |
| Abrasion group | MSZ EN 660-1 | class | T |
| Fire resistance | EN 13501-1 | class | Bfl-s1 |
| | BS 476 | | Class 1 |
| | Gost 30402-94 | | G1 |
| Impact sound reduction | EN ISO 140-8 | DL _w (dB) | 18 |
| Slip resistance | DIN 51130 | | R9 |
| | AS/NZS 4586 | | R10 |
| Electrical resistance | EN 1815 | kV | < 2 |
| | EN 1081 | Ω | ≤ 10 ⁹ |
| Chemical resistance | EN 423 | | ✓ |
| Bacterial resistance | EN ISO846:1999 | | ✓ |
| Castor chair resistance | EN 425 | | ✓ |
| Surface treatment | |  | CLP |
| Anti-bacterial and fungicid treatment | |  | graboSAN |
| Enviromental attributes | |  | Solvent and heavy metal free product |
| Seaming method | | | heat or cold weld |
| Warranty | | year | 7 |
| CE MARKING | EN 14041 | | ✓ |