






DESCRIPTION			
Total thickness	EN ISO 24346 [EN 428]	mm	6.00
Thickness of wearlayer	EN ISO 24340 [EN 429]	mm	2
Weight	EN ISO 23997 [EN 430]	g/m <sup>2</sup>	9365
Tile size	EN ISO 24342 [EN 427]	mm	635 x 635 GTI Connect
			600 x 600 GTI Cleantech (without dovetail) (1)
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 10582 [EN 649]
European classification	EN ISO 10874 (EN 685)	class	34 - 43
Fire rating	EN 13 501-1	class	B <sub>fl</sub> -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet: ramp test with oil	DIN 51130	class	R10
Pendulum test	BS7976	-	<b>HSE 36 compliant</b> Béton emboss References : Ermellino – Ora – Bora – Libeccio – Grecale – Scirocco – Tramontana
			NO Rice emboss References : Red – Blue – Green – Yellow – Black – Light Grey – Dark Grey – Carbon – Magma – Saphir – Aluminium – Titanium – Peler – Levente – Ponente – Maestrale
PERFORMANCE			
Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 2
Wear group	NF 189	group	T
Type Binder content	EN ISO 10582	type	I
Dimensional stability	EN ISO 23999 [EN 434]	%	≤ 0.15
Residual indentation	EN ISO 24343-1 [EN 433]		≤ 0.10
Castor chair test (type W)	ISO 4918 (EN 425)	-	OK
Shore hardness	EN ISO 868	H <sub>D</sub>	≥ 55
Shifting resistance	CAHIER CSTB 3562	N/mm <sup>2</sup>	≥ 30
Thermal conductivity	EN ISO 10456 (EN12524)	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR+
Chemical products resistance	EN ISO 26987 [EN 423]	-	OK
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 100
Certification	-	-	Floorscore®
CE MARKING			
	EN 14041	-	  
		-	

(1) Available upon request