## illiken

## **SEGUE**

## Segue

Construction

Tufted, Textured Loop

Tile Size

1 m x 1 m (39.4" x 39.4")

Yarn Type

Milliken-Certified WearOn® Nylon Type 6

Stain Repel / Stain Resist / Soil Release

StainSmart®

Antimicrobial

AlphaSan® AF Built-In Protection†

Dye Method

Millitron®

**Tufted Face Weight** 

 $20 \text{ oz/yd}^2 (678 \text{ g/m}^2)$ 

Gauge

1/8

**Stitches Per Inch** 

8.0

**Tufts** 

64/in<sup>2</sup> (991/100 cm<sup>2</sup>)

**Finished Pile Height** 

0.09" (2.29 mm)

**Average Density (Finished)** 

8,000

**Standard Backing** 

PVC-Free Comfort Plus® ES Cushion

Available with TractionBack®

**Recycled Content by Total Weight** 

ES Backing: 26% Pre-Consumer ESP Backing: 17% Pre-Consumer, 9% Post-Consumer

**Nominal Total Thickness** 

0.35" (8.9 mm)

**Nominal Total Weight** 

 $106 \text{ oz/yd}^2 (3,594 \text{ g/m}^2)$ 

Flammability (Radiant Panel **ASTM-E-648**)

≥ 0.45 (Class I)

**Smoke Density (NFPA-258-T or** 

**ASTM-E-662)** 

< 450

**Methenamine Pill Test (CPSC FF-1-70** or **ASTM D 2859** 

Self-Extinguishing

**Lightfastness (AATCC 16E)** 

> 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20% R.H.,70° F.

≤ 3.5 KV, Permanent Conductive Fiber

**Texture Appearance Retention Rating** (TARR)

Severe Traffic End-Use Applications

**Recommended Maintenance** 

MilliCare® Textile and Carpet Care

Service Network

Indoor Air Quality—CRI Green Label

Plus™

GLP0793, Carpet Category 5Y

Recommended Installation Method(s)

Monolithic

## WARRANTIES

Lifetime Antimicrobial Protection (AlphaSan®) Lifetime Face Fiber Wear Lifetime Antistatic Lifetime Floor Compatibility Lifetime Color Pattern Permanency

Lifetime Floor Release Lifetime Cushion Resiliency Lifetime Moisture Resistance Lifetime Delamination of Backing Lifetime Staining/Soiling (StainSmart®)

Lifetime Dimensional Stability Lifetime Tuft Bind Lifetime Edge Ravel Flammability









This cushion-back carpet tile product is covered by one or more patents, published applications and/ or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.