

DESCRIPTION

Total thickness	EN ISO 24346 [EN 428]	mm	1.5
Weight	EN ISO 23997 [EN 430]	g/sq.m	2520
Width of sheet	EN ISO 24341 [EN 426]	cm	200
Length of sheet	EN ISO 24341 [EN 426]	lm	20

CLASSIFICATION

Norm / Product specification	-	-	EN ISO 10581 (EN 649)
European classification	EN ISO 10874 (EN 685)	class	23-31
Fire rating	EN 13 501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2




PERFORMANCE

Wear resistance	EN 660.2	mm ³	≤ 15
Wear Group	NF 189	group	F
Type Binder content	EN ISO 10581	type	II
Dimensional stability	EN ISO 23999 [EN 434]	%	≤ 0.40
Residual indentation	EN ISO 24343-1 [EN 433]	mm	≈ 0.03
Castor chair test (type W)	ISO 4918 (EN 425)	-	OK
Thermal conductivity	EN ISO 10456 (EN12524)	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR
Chemical products resistance	EN ISO 26987 [EN 423]	class	OK

ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10
--------------------	-------------	--------------------	------

CE MARKING

	EN 14041	-	  
		-	