






DESCRIPTION			
Total thickness	EN ISO 24346 [EN 428]	mm	2.00
Weight	EN ISO 23997 [EN 430]	g/sq.m	3300
Width of sheet	EN ISO 24341 [EN 426]	cm	200
Length of sheet	EN ISO 24341 [EN 426]	lm	20
Tile size	EN ISO 24342 [EN 427]	mm	300 x 300* / 608 x 608
Number of tiles per package	-	-	50 / 20
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 10581 (EN 649)
European classification	EN ISO 10874 (EN 685)	class	34 - 43
Fire rating	EN 13 501-1	class	B <sub>fl</sub> -s1
Static electrical propensity	EN 1815	kV	< 2
PERFORMANCE			
Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 7.5
Wear Group	NF 189	group	M
Type Binder content	EN ISO 10581	type	II
Dimensional stability	EN ISO 23999 [EN 434]	%	sheet ≤ 0.40 tile ≤ 0.25
Impact sound insulation	EN ISO 717-2	dB	4
Residual indentation	EN ISO 24343-1 [EN 433]	mm	~ 0.03
Castor chair test (type W)	ISO 4918 (EN 425)	-	OK
Thermal conductivity	EN ISO 10456 (EN12524)	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR
Chemical products resistance	EN ISO 26987 [EN 423]	class	OK
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 10
CE MARKING			
	EN 14041	-	  
		-	

\* upon special request