

Fabrikatiemethode Mode de fabrication Herstellungsverfahren Manufacturing process	Getuft, 1/10" lussenpool Tufté, 1/10" velours bouclé Getuftet, 1/10" Schlinge Tufted, 1/10" loop pile				
Samenstelling van de pool Composition du velours Nutzschicht Pile composition	50 % wol – 40% PP – 10% PES meltbound 50% % laine – 40% PP – 10% PES meltbound 50% % wolle – 40% PP – 10% PES meltbound 50% wool – 40% PP – 10% PES meltbound				
Tuftdoek Support Trägergewebe Primary backing	100 % PP				
Rug Dossier Rücken Secondary backing	Actionback	4340 4 + 5 m	Crème Crème Crème Crème	4332 4 + 5 m	Zand Sable Sand Sand
Poolhoogte Hauteur du velours Polhöhe Pile height	4 mm	4334 4 + 5 m	Duin Dune Düne Dune	4336 4 + 5 m	Licht grijs Gris clair Hell grau Light grey
Totale hoogte Hauteur totale Gesamthöhe Total height	6,5 mm	4328 4 + 5 m	Mid grijs Gris moyen Mittel	4338 4 + 5 m	Wit Blanc Weiss White
Aantal noppen Nombre de points Noppenzahl Tuft density	113 500/m <sup>2</sup>	4340STR 4 + 5 m	Crème Crème Crème Crème	4332STR 4 + 5 m	Zand Sable Sand Sand
Poolgewicht Poids du velours Polgewicht Pile weight	730 g/m <sup>2</sup>	4334STR 4 + 5 m	Duin Dune Düne Dune	4336STR 4 + 5 m	Licht grijs Gris clair Hell grau Light grey
Totaal gewicht Poids total Gesamtwicht Total weight	1 800 g/m <sup>2</sup>	4328STR 4 + 5 m	Mid grijs Gris moyen Mittel grau Mid grey		
Warmte isolatie Résistance à la conductibilité de chaleur Wärmedurchlasswiderstand Resistance of heat conduction	ISO 8302 0,14 m <sup>2</sup> K/W (theoretisch)	Tog rating 1.4 (AB)			
Gebruik Utilisation Verwendungsbereich Suitability	Huishoudelijk : normaal gebruik Usage d'habitation modéré Wohnen : normal Beanspruchung Domestic : general duty				

Bij verwijming : enkel gebruik van EC1-lijmen ! / En cas de pose collée : seulement utilisation des colles EC1 !  
Bei geklebter Verlegung : nur EC1-Klebstoffe verwenden ! / In case of adhesion : only use of EC1 glues !

We reserve the right to modify the characteristics of this product for quality improvement.

