



- The flooring shall be Polyflor Colonia PUR, as supplied by Polyflor Ltd. of Manchester, England.
- The flooring shall be flexible PVC tile and plank flooring in 2.0mm thickness.
- It shall have the following laminated construction: circa 0.2mm clear PVC wear layer, circa 0.07mm print film layer, and circa 1.73mm backing ply.
- The flooring shall feature a high quality, cross-linked polyurethane reinforcement to provide superior cleaning benefits, life cycle maintenance savings and optimum appearance retention.



- In accordance with EN 649 and EN ISO 10582, the in-use classification must be 22 as described in EN 685 and EN ISO 10874: i.e. domestic areas with medium use.
- In respect of flame spread, the flooring shall have been fully tested to EN 13501-1 and certified as having Class Bfl-S1.
- The product is classed as DS (dry slip) when tested to EN 13983. It also achieves an R10 rating when tested to DIN 51130 and AS/NZS 4586. For safety flooring with sustainable wet slip resistance, refer to Expona Control or the Polysafe ranges.
- The product's weight should not be more than 3680g/m<sup>2</sup>.



- The flooring will achieve a BRE Global Environmental A rating ENP 429 in the Green Guide to Specification.
- The manufacturer should provide a facility to take back and recycle waste vinyl flooring material through the Recofloor scheme.
- Colonia achieves a very low VOC emissions result when tested to AgBB standards, is certified by Eurofins as achieving Indoor Air Comfort Gold and is also a FloorScore certified product.



- The supplier of the floorcovering must be in possession of a valid quality systems certificate, showing compliance with BS EN ISO 9001.
- The manufacturer of the floorcovering must be in possession of a valid environmental certificate, showing compliance with ISO 14001.



- A moisture test must be carried out, to ensure that the subfloor has dried out to a level consistent with the application of vinyl flooring. The test should be carried out using a hygrometer, in accordance with the instructions in BS 8203. The result should not exceed 75%RH, once equilibrium has been achieved.
  - The adhesive used must be approved by Polyflor, to ensure full product compatibility.
  - Products must be fully conditioned to the environment in which they are to be installed. See Polyflor installation instructions for details.
  - Installation must be carried out in accordance with BS 8203 and the instructions of Polyflor.
  - Suitable for use with underfloor heating up to 27°C. See Polyflor installation instructions for details.
- NOTE:** The subtle blending of shades and graining variation can best be obtained by the random shuffling of 3-4 packs of tiles.



- Polyflor Colonia PUR is ideal for use in the home in living rooms, kitchens, bathrooms, bedrooms, dining rooms, entrance halls and conservatories. On-floor temperatures in conservatories can become quite high. It is strongly advised that, in such situations, a Polyflor recommended high temperature adhesive is used. For further information and advice on specific applications, consult Polyflor Customer Technical Services on +44 (0)161 767 1912, or email tech@polyflor.com.




- At the date of issue the data presented is correct. However, Polyflor Ltd. reserve the right to make changes which do not adversely affect performance or quality.

COLONIA™  
FLOORING COLLECTION



PRODUCT  
SPECIFICATION



POLYFLOR LTD. PO BOX 3 RADCLIFFE NEW ROAD WHITEFIELD MANCHESTER M45 7NR UK  
 UK SALES DIRECT: +44 (0)161 767 1122 UK SAMPLE REQUESTS: +44 (0)161 767 2551  
 EXPORT SALES DIRECT: +44 (0)161 767 1913 TECHNICAL SUPPORT: +44 (0)161 767 1912  
 RECEPTION: +44 (0)161 767 1111 UK FAX: +44 (0)161 767 1128  
 EXPORT FAX: +44 (0)161 767 1166 E-MAIL: INFO@POLYFLOR.COM  
 WEBSITE: WWW.POLYFLOR.COM

*James Halstead*  
FLOORING



2011

POLYFLOR™  
COVERING THE WORLD