


Fabrikatiemethode Mode de fabrication Herstellungsverfahren Manufacturing process	Getuft,5/32" lussenpool Tufté, 5/32" velours bouclé Getuftet, 5/32" Schlinge Tufted, 5/32" loop pile				
Samenstelling van de pool Composition du velours Nutzschicht Pile composition	10 % wol - 90 % PP 10 % laine - 90 % PP 10 % Wolle - 90 % PP 10 % wool - 90 % PP				
Tuftdoek Support Trägergewebe Primary backing	100 % PP				
Rug Dossier Rücken Secondary backing	Actionback + Felt	106 4 + 5 m	Creme	3326 4 + 5 m	Sand
Poolhoogte Hauteur du velours Polhöhe Pile height	5 mm	3327 4 + 5 m	Beige	3328 4 + 5 m	Mocca
Totale hoogte Hauteur totale Gesamthöhe Total height	6,5 mm(AB) 8mm (felt)	3498 4 + 5 m	Light Brown	3496 4 + 5 m	Dune
Aantal noppen Nombre de points Noppenzahl Tuft density	85 000/m²				
Poolgewicht Poids du velours Polgewicht Pile weight	600 g/m²				
Totaal gewicht Poids total Gesamtgewicht Total weight	1 600 g/m² (AB) 1 950 g/m²(felt)				
Warmte isolatie Résistance à la conductibilité de chaleur Wärmedurchlasswiderstand Resistance of heat conduction	DIN 52612	0,13 m² K/W (theoretisch)			
Gebruik Utilisation Verwendungsbereich Suitability	Huishoudelijk : normaal gebruik Résidentiel : usage normal Wohnen : mittlere Beanspruchung Domestic : medium duty				

Bij verlijming : enkel gebruik van lijmen zonder hoogkokende oplosmiddelen ! / En cas de pose collée : seulement utilisation des colles écologiques !
Bei geklebter Verlegung : nur hochsiederefreie Klebstoffe verwenden ! / In case of adhesion : only use of ecological glues !
We reserve the right to modify the characteristics of this product for quality improvement.



ACTIONBACK



VLIES



Prodis Number Felt backing = EF047741