

Sisamo Stripe


Specification according to EN 1307

Type of manufacture	ISO 2424	Tufted 1/8 "
Aspect	ISO 2424	Loop pile
Dye method		Solution dyed
Width	CEN/TS 14159 cm	400 / 13' 1.5"
Primary backing	ISO 2424	Polypropylene fleece
Secondary backing	ISO 2424	Polypropylene woven - Sandwich Backing
Pile fibre composition	ISO 2424	BCF Polyamide 6
Total thickness	ISO 1765 mm	7.5 inch 0.30
Effective pile thickness	ISO 1766 mm	4.5 inch 0.18
Total mass	ISO 8543 g/m ²	2650 oz/yd ² 78.2
Total pile mass	ISO 2424 g/m ²	1130 oz/yd ² 33.4
Effective pile mass	ISO 8543 g/m ²	800 oz/yd ² 23.6
Pile density	ISO 8543 g/cm ³	0.180 lb/in ³ 0.0065
Number of tufts	ISO 1763 /dm ²	1580 /yd ² 132104
Stroll test	ISO 6356 kV	≤ 2.0
Vertical resistance	ISO 10965 Ohm	-
Horizontal resistance	ISO 10965 Ohm	-
Classification for use		33 Commercial - heavy use
Luxury rating		LC 3
Impact sound reduction ΔL_W	ISO 140-8 dB	26
Sound absorption	EN ISO 354 freq. Hz	125 250 500 1000 2000 4000
		α_s 0.01 0.02 0.09 0.21 0.51 0.60
Noise reduction	EN ISO 354 α_w	0,20(--H)
Thermal resistance	ISO 8302 m ² .K/W	0.050
Flammability	EN 13501-1	Bfl - s1

EN 14041:2004
05

Manufactured by:

Desso NV
Robert Ramlotstraat 89
B - 9200 Dendermonde



Desso flooring products are to be installed in full accordance with Desso's installation instructions and recognised trade standards.

An effective, regular cleaning and maintenance programme is vital for retaining a high appearance level.

Desso flooring products should only be used as floorcoverings.

Note: Desso reserve the right to amend this specification without giving prior notice.

For the latest versions of the technical specifications, check our internet site: www.desso.com