

Underlay Technical Specification

Item Code: TASENSATION


Issue Date: 4/3/2014

Issue No. 3

Polyurethane Rebond

Suitable for the stretch-fit installation of carpets

End Use Classification (BS 5808: 1991): L/U, Luxury Use



Standard Specifications

Nominal density†	145 kg/m ³
Nominal square weight †	1595 g/m ² (47 oz/yd ²)
Nominal roll weight†	24.3 kg (53.0 lbs)
Roll area*	15.07m ² (1.37m x 11.0m)

BS 5808: 1991

End Use Classification	L/U, Luxury Use	
Nominal thickness†	11.00mm	BS 4051
Work of compression Minimum 50 J/m ²	>200 J/m ²	BS 4908 & BS 4052
Retention of work of compression (min 40%)	>90 %	BS 4908 & BS 4052
Loss in thickness after dynamic loading (max 15%)	<5 %	BS 4052
Loss in thickness after static loading (max 15%)	<5 %	BS 4939
Resistance to cracking (not greater than 50mm)	Pass	BS 5808

Flammability

Hot metal nut test (tested in Interfloor laboratory)	Pass	BS 4790 & BS 5287
--	------	-------------------

Other Specifications

Odour	No objectionable odour	
Colour / backing	Green / printed Textron® backing	
Packaging	Green film / black print	
Thermal resistance	2.89 togs	BS 4745
Impact sound reduction (Delta Lw)	43 dB	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria	

Certification



Guarantee

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification.

Notes

* The nominal roll dimensions have been quoted. These may vary slightly, but will still equate to the area quoted. This does not constitute a manufacturing specification. It details important performance and physical characteristics only.

† ±5%

‡ Value derived from similar product test results