TECHNICS 6

TREDAIRE

Underlay Technical Specification

Item Code: TATECH6

Issue Date: 12/3/2013

Issue No. 10





Certification





Guarantee

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification.



Sponge Rubber

Suitable for underfloor heating Suitable for flame retardant applications Suitable for the double-stick and stretch-fit installation of carpets End Use Classification (BS 5808: 1991): HC/U, Heavy Contract Use

3153 g/m² (93 oz/yd²)
47.5 kg (106 lbs)
15.07m ² (1.35m x 11.16m)

BS 5808: 1991

End Use Classification	HC/U, Heavy Contract Use	
Nominal thickness [†]	6.00mm	BS 4051
Mean original thickness from nominal thickness (max. 12%)	3.0 %	BS 4051
Difference between max. & min. original thickness (max. 3mm)	0.3 mm	BS 4051
Work of compression Minimum 50 J/m ²	119 J/m²	BS 4908 & BS 4052
Retention of work of compression (min 40%)	86 %	BS 4908 & BS 4052
Compression after dynamic loading	3.0 mm	BS 4908 & BS 4052
Breaking strength (length/width) min. 40N	282N / 162N	BS 2576
Extension under force (length/width) max. 10%@ 40N	0.8% / 0.5%	BS 2576
Loss in thickness after dynamic loading (max 15%)	3.8 %	BS 4052
Loss in thickness after static loading (max 15%)	4.2 %	BS 3939
Resistance to cracking (not greater than 50mm)	Pass	BS 5808

Flammability Hot metal nut test (Not greater than 50mm) Low radius of effects of ignition Critical radiant flux Category 1 (0.53W/cm²) Reaction to fire classification (tested in conjunction with Brintons Axminster 1028 carpet) Cfl-s1 Tested to Russian GOST FR Test Classification KM5 GOST 3

Classification KM5 GOST 30244-94, GOST 30402-96 GOST 51032-97, GOST 12.1.044-89 (item 4.18), GOST 12.1.044-89 (item 4.20)

BS 4790 & BS 5287

rated to EN13501-1

ASTM E648 / NFPA253

Tested to ENISO9239-1 & 11925-2,

Other Specifications	
Odour	No objectionable odour
Antimicrobial and mildew resistant	Yes
Colour / backing	Black / printed Textron [®] backing
Packaging	Red film / white print
Thermal resistance	0.66 togs BS 4745
Impact sound reduction (Delta Lw)	31 dB BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria

Notes

The nominal roll dimensions have been quoted. These may vary slightly, but will still equate to the area quoted. This does not constitute a manufacturing specification. It details important performance and physical characteristics only.

† ±5%

Interfloor Ltd., Broadway, Haslingden, Rossendale, Lancashire, BB4 4LS. Tel: +44(0)1706 213131 Fax: +44(0)1706 260800 Web: www.interfloor.com International Enquiries: Telephone: +44(0)1706 238824 Fax: +44(0)1706 225114