

Underlay Technical Specification

Item Code: TAENERGY2

Issue Date: 13/3/2013

Issue No. 9

Sponge Rubber Textured Flat

Suitable for the stretch-fit installation of carpets

End Use Classification (BS 5808: 1991): GD/U, General Domestic Use



Nominal square weight †	2576 g/m² (76 oz/yd²)
Nominal roll weight [†]	38.82 kg (86 lb)
Roll area*	15.07m ² (1.33m x 11.33m)



End Use Classification	GD/U, General Domestic Use	
Nominal thickness [†]	7.00 mm	BS 4051
Work of compression Minimum 50 J/m²	118 J/m²	BS 4908 & BS 4052
Retention of work of compression (min 40%)	70 %	BS 4908 & BS 4052
Compression after dynamic loading	4.1 mm	BS 4908 & BS 4052
Loss in thickness after dynamic loading (max 15%)	4.8 %	BS 4052
Loss in thickness after static loading (max 15%)	9.3 %	BS 3939
Resistance to cracking (not greater than 50mm)	Pass	BS 5808

Flammability

Hot metal nut test (tested in Interfloor laboratory)	Pass	BS 4790 & BS 5287
Critical radiant flux	Category 1 (0.53W/cm²)	ASTM E648 / NFPA253
Russian GOST FR Test	GOST 51032-97, GO	30244-94, GOST 30402-96 OST 12.1.044-89 (item 4.18), OST 12.1.044-89 (item 4.20)

Other Specifications

Odour	No objectionable odour
Antimicrobial and mildew resistant	Yes
Colour / backing	Red / printed Textron® backing
Packaging	Grey film / red print
Thermal resistance	1.01 togs BS 4745
Impact sound reduction (Delta Lw)	30dB BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria

	LD.# CC-8478
LD.# CC-8478	MEETS LOW VO

Certification





Guarantee

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification.

Notes

- * The nominal roll dimensions have been quoted. These may vary slightly, but will still equate to the area quoted. This does not constitute a manufacturing specification. It details important performance and physical characteristics only.
- † ±5%
- [‡] Value derived from similar product test results

