

ARCADIA

Terrain

Modular Tile

Construction

Tufted, Loop

Tile Sizes

1 m x 1 m (39.4" x 39.4")

25 cm x 1 m (9.85" x 39.4")

Yarn Type

Universal Fibers® Solution-Dyed Nylon
Type 6,6

Stain Repel / Stain Resist / Soil Release

StainSmart®

Antimicrobial

AlphaSan® AF Built-In Protection†

Dye Method

Solution Dyed

Tufted Face Weight

14.4 oz/yd² (488 g/m²)

Gauge

1/12

Stitches Per Inch

9.2

Tufts

110/in² (1,704/100 cm²)

Finished Pile Height

0.156" (3.96 mm)

Finished Pile Thickness

0.092" (2.34 mm)

Average Density (Finished)

5,630

Standard Backing

PVC-Free Underscore® ES Cushion
Available with TractionBack®

Recycled Content by Total Weight

ES Backing: 39.6% Pre-Consumer,
0.0% Post-ConsumerESP Backing: 29.1% Pre-Consumer,
10.7% Post-Consumer

Nominal Total Thickness

0.32" (8.1 mm)

Nominal Total Weight

88.4 oz/yd² (2,997 g/m²)

Flammability (Radiant Panel)

ASTM-E-648)

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or

ASTM-E-662)

≤ 450

Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20% R.H., 70° F.

≤ 3.5 KV, Permanent Conductive Fiber

Texture Appearance Retention Rating (TARR)

Heavy Traffic End-Use Applications

Recommended Maintenance

MilliCare® Textile and Carpet Care
Service Network

Indoor Air Quality—CRI Green Label Plus™

GLP7205, Carpet Category 13X

Recommended Installation Method(s)

Monolithic, Ashlar

WARRANTIES

Lifetime Antimicrobial Protection (AlphaSan®)

Lifetime Face Fiber Wear

Lifetime Antistatic

Lifetime Floor Compatibility

Lifetime Color Pattern Permanency

Lifetime Floor Release

Lifetime Cushion Resiliency

Lifetime Moisture Resistance

Lifetime Delamination of Backing

Lifetime Staining/Soiling (StainSmart®)

Lifetime Dimensional Stability

Lifetime Tuft Bind

Lifetime Edge Ravel

Flammability



This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.