

NEW SLANT

Trisect

Modular Tile

Construction

Tufted, Textured Loop

Tile Size

25 cm x 1 m (9.85" x 39.4")

Yarn TypeUniversal Fibers® Solution-Dyed Nylon
Type 6,6**Stain Repel / Stain Resist / Soil Release**

StainSmart®

Antimicrobial

AlphaSan® AF Built-In Protection†

Dye Method

Solution Dyed

Tufted Face Weight28 oz/yd² (949 g/m²)**Gauge**

1/12

Stitches Per Inch

12.0

Tufts144/in² (2,230/100 cm²)**Finished Pile Height**

0.19" (4.83 mm)

Finished Pile Thickness

0.14" (3.56 mm)

Average Density (Finished)

7,888

Standard BackingPVC-Free Comfort Plus® ES Cushion
Available with TractionBack®**Recycled Content by Total Weight**ES Backing: 41.8% Pre-Consumer,
0.0% Post-Consumer
ESP Backing: 32.3% Pre-Consumer,
9.6% Post-Consumer**Nominal Total Thickness**

0.42" (10.7 mm)

Nominal Total Weight125.6 oz/yd² (4,259 g/m²)**Flammability (Radiant Panel****ASTM-E-648)**

≥ 0.45 (Class I)

Smoke Density (NFPA-258-T or**ASTM-E-662)**

≤ 450

Methenamine Pill Test (CPSC FF-1-70**or ASTM D 2859**

Self-Extinguishing

Lightfastness (AATCC 16E)

≥ 4.0 at 80 Hours

Crocking (AATCC 165)

≥ 4.0 Wet or Dry

Static Electricity (AATCC-134) 20%**R.H., 70° F.**

≤ 3.5 KV, Permanent Conductive Fiber

Texture Appearance Retention Rating (TARR)

Severe Traffic End-Use Applications

Recommended MaintenanceMilliCare® Textile and Carpet Care
Service Network**Indoor Air Quality—CRI Green Label****Plus™**

GLP7205, Carpet Category 13X

Recommended Installation Method(s)

Planks

WARRANTIES

Lifetime Antimicrobial Protection (AlphaSan®)

Lifetime Face Fiber Wear

Lifetime Antistatic

Lifetime Floor Compatibility

Lifetime Color Pattern Permanency

Lifetime Floor Release

Lifetime Cushion Resiliency

Lifetime Moisture Resistance

Lifetime Delamination of Backing

Lifetime Staining/Soiling (StainSmart®)

Lifetime Dimensional Stability

Lifetime Tuft Bind

Lifetime Edge Ravel

Flammability



This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.