

Woven Touch

Construction	Tufted, Textured Loop
Face Fiber	WearOn® Nylon
Dye Method	Millitron®
Soil and Stain Protection	MilliGuard®
Antimicrobial	AlphaSan® Built-In Protection
Gauge	1/8
Rows	11.8/in.
Tuft Density	94.4/sq.in.
Finished Pile Height	0.11 in. (2.8 mm.)
Density Factor	496,730
Average Density	6,218
Secondary Backing	PVC-Free Underscore™ ES cushion
Tile Size	50cm x 50cm (19.7 x 19.7 in.)
Flammability (Radiant Panel ASTM-E-648)	≥ 0.45 (Class I)
Smoke Density (NFPA-258-T or ASTM-E-662)	≤ 450
Methenamine Pill Test (CPSC FF-1-70 or ASTM D 2859)	Self-Extinguishing
Lightfastness (AATCC 16E)	≥ 4.0 at 80 hrs.
Crocking (AATCC 165)	≥ 4.0 wet or dry
Static Electricity (AATCC-134) 20% R.H., 70° F.	≤ 3.5 KV, Permanent Conductive Fiber
Dimensional Stability - Aachener Test (DIN Std 54318)	≤ 0.2%
Texture Appearance Retention Rating (TARR)	Severe Traffic End-Use Applications
Recommended Maintenance	Capture® Carpet and Fabric Care
Indoor Air Quality - CRI Green Label Plus™	GLP0793, Carpet Category 5Y

Design Copyright - Milliken & Company

This cushion-back carpet tile product is covered by one or more patents, published applications and/or patents pending.

Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available upon request.



Warranties:

Lifetime Antimicrobial Protection (AlphaSan®)	Lifetime Face Fiber Wear
Lifetime Antistatic	Lifetime Floor Compatibility
Lifetime Color Pattern Permanency	Lifetime Floor Release
Lifetime Cushion Resiliency	Lifetime Moisture Resistance
Lifetime Delamination of Backing	Lifetime Staining/Soiling
Lifetime Dimensional Stability	Lifetime Tuft Bind
Lifetime Edge Ravel	Flammability